

# HASTELLOY<sup>®</sup> C-2000<sup>®</sup> alloy

## Hardness

<b>Form</b>	<b>Hardness, HRBW</b>	<b>Typical ASTM Grain Size</b>
Sheet	87	3 - 5
Plate	88	1 - 4
Bar	84	0 - 4

All samples tested in solution-annealed condition.

HRBW = Hardness Rockwell "B", Tungsten Indentor.