

# HASTELLOY<sup>®</sup> N alloy

## Average Room Temperature Hardness

Form	Condition	Aging		HRB
		°F	h	-
Sheet	Heat-treated at 2150°F (1177°C), RAC	-	-	96
		1500	4	92
		1500	8	97
		1500	16	96
		1500	32	97
		1500	64	99
		1500	128	96

HRB = Hardness Rockwell "B".