

HAYNES[®] 188 alloy

Hardness Data

Solution Annealed Room Temperature Hardness

Form	Hardness, HRB	Typical ASTM Grain Size
Sheet	98	5 - 7.5
Plate	98	4 - 8
Bar	96	3.5 - 7.5

All samples tested in solution-annealed condition

HRB = Hardness Rockwell "B"