

HAYNES[®] HR-160[®] alloy

Physical Metallurgy

-	Typical Grain Size	Average Hardness
Plate	3 - 4½	89
Bar	2 - 3	85
Sheet	3½ - 4½	88

