

HASTELLOY[®] C-4 alloy

Hardness

Form	Hardness, HRBW	Typical ASTM Grain Size
Sheet	92	6 - 7.5
Plate	90	4 - 6

All samples tested in solution-annealed condition.

HRBW = Hardness Rockwell "B", Tungsten Indentor.