

HASTELLOY[®] N alloy

Boiler Code Design Data

Metal Temperature Not Exceeding		Maximum Allowable Stress Values, psi All Material Other Than Boiling	Boiling
°F	°C	-	-
100	38	25,000	10,000
200	93	24,000	9,300
300	149	23,000	8,600
400	204	21,000	8,000
500	260	20,000	7,700
600	316	20,000	7,500
700	371	19,000	7,200
800	427	18,000	7,000
900	482	18,000	6,800
1000	538	17,000	6,600
1100	593	13,000	6,000
1200	649	6,000	3,500
1300	704	3,500	1,600