

HAYNES[®] HR-120[®] alloy

Hardness and Grain Size

Solution-annealed Room Temperature Hardness

Form	Hardness, HRB	Typical ASTM Grain Size
Sheet	88	3.5 - 5
Plate	87	0 - 5
Bar	84	0 - 4.5

HRB= Hardness Rockwell "B"