

HAYNES[®] 25 alloy

Hardness and Grain Size

Form	Hardness, HRB	Typical ASTM Grain Size
Sheet	97	3.5 - 5.5
Plate	99	3.5 - 5
Bar	98	3.5 - 5

All samples tested in solution-annealed condition

HRB = Hardness Rockwell "B"