

# HAYNES<sup>®</sup> 25 alloy

## Hardness and Grain Size

<b>Form</b>	<b>Hardness, HRBW</b>	<b>Typical ASTM Grain Size</b>
Sheet	97	3.5 - 5.5
Plate	99	3.5 - 5
Bar	98	3.5 - 5

All samples tested in solution-annealed condition

HRBW = Hardness Rockwell "B", Tungsten Indentor.

[Print Page](#)