

HASTELLOY[®] W alloy

Heat Treatment

Weld Deposits (A), Wrought Bar (B)

(A) None (B) 2165 °F (1185 °C)/15 minutes/WQ