

HAYNES[®] 230[®] alloy

Hardness and Grain Size

Solution Annealed Room Temperature Hardness

| Form | Hardness, HRBW | Typical ASTM Grain Size |
|-------------|---------------------------|--------------------------------|
| Sheet | 92 | 4 - 6.5 |
| Plate | 92 | 3 - 5 |
| Bar | 90 | 3 - 5 |

HRBW = Hardness Rockwell "B", Tungsten Indentor.