

HASTELLOY® C-2000® alloy

Corrosion Resistance of Welds

To assess the resistance of welds to corrosion, Haynes International has chosen to test all-weld-metal samples, taken from the quadrants of cruciform assemblies, created using multiple gas metal arc (MIG) weld passes. Predictably, the inhomogeneous nature of weld microstructures leads generally to higher corrosion rates (than with homogeneous, wrought products). Nevertheless, HASTELLOY® C-2000® alloy exhibits excellent resistance to the key, inorganic acids, even in welded form, as shown in the following table:

Chemical	Concentration	Temperature	Corrosion Rate				
			Weld Metal		Wrought Base Metal		
	wt. %	°F	°C	mpy	mm/y	mpy	mm/y
H ₂ SO ₄	30	150	66	0.2	0.01	<0.1	<0.01
H ₂ SO ₄	50	150	66	0.3	0.01	<0.1	<0.01
H ₂ SO ₄	70	150	66	2.4	0.06	0.2	0.01
H ₂ SO ₄	90	150	66	2.9	0.07	0.6	0.02
HCl	5	100	38	0.1	<0.01	0.1	<0.01
HCl	10	100	38	2.1	0.05	<0.1	<0.01
HCl	15	100	38	2.4	0.06	7.0	0.18
HCl	20	100	38	8.0	0.20	6.3	0.16
HNO ₃	30	Boiling		3.8	0.10	3.5	0.09

[Print Page](#)