

# HAYNES<sup>®</sup> X-750 alloy

## Heat Treatment

### Sheet and Strip

1900°F (1040°C)/Bright-anneal + 1350°F (730°C)/8 h/FC to 1150°F (620°C)/8 h/AC