

MULTIMET[®] alloy

Hardness

Form	Hardness, HRBW	Typical ASTM Grain Size
Sheet	90	4.5 - 6.5
Plate	92	3 - 6.5
Bar	89	3 - 5

HRBW = Hardness Rockwell "B", Tungsten Indentor.

All samples tested in solution-annealed condition