

HASTELLOY[®] G-35[®] alloy

Hardness

Form	Hardness, HRBW	Typical ASTM Grain Size
Sheet	87	3.5 - 5
Plate	87	2 - 4.5
Bar	82	1 - 4

All samples tested in solution-annealed condition.

HRBW = Hardness Rockwell "B", Tungsten Indentor.