

HAYNES[®] NS-163[®] alloy

Heat Treatment

Solution Heat Treatment:

Typical Solution Annealing Temperature: 2100 to 2150°F (1150 to 1177°C) in dry hydrogen.

NDS (Nitride Dispersion Strengthening) Treatment:

NDS treatments have been developed for this alloy. Please contact Haynes International for more detailed information.