

HASTELLOY[®] G-35[®] alloy

Impact Strength

Plate Thickness		Test Temperature		Impact Strength*	
in	mm	°F	°C	ft.lbf	J
0.75	19.1	RT	RT	>264	>358

*Charpy V-Notch Samples