

HASTELLOY[®] X alloy

Hardness and Grain Size

Room Temperature Hardness of Material Solution Annealed at 2150°F

Form	Hardness, HRBW	Typical ASTM Grain Size
Sheet	86	3 - 5
Plate	87	3.5 - 6
Bar	88	2 - 5

HRBW = Hardness Rockwell "B", Tungsten Indentor.