

HAYNES[®] 242[®] alloy

Hardness and Grain Size

Solution Annealed Room Temperature Hardness

Form	Hardness, HRBW	Typical ASTM Grain Size
Sheet	92	5 - 6.5
Plate	94	4 - 6.5
Bar	90	3.5 - 6

HRBW= Hardness Rockwell "B", Tungsten Indentor.