

HASTELLOY[®] W alloy

Guided Bend Test Results

1/2 inch (12.7) Plate Weldments (GTAW) Using Alloy W Filler

Base Materials	Bend Radius	Results
188/ MULTIMET [®]	2t	No Cracks
625/ 718	2t	No Cracks
304 SS/ Carbon Steel	2t	No Cracks