

HAYNES[®] HR-235[®] alloy

Heat Treatment

Wrought HAYNES[®] HR-235[®] alloy is furnished in the solution heat treated condition, unless otherwise specified. The alloy is normally solution heat-treated at 2100-2150°F (1149-1177°C) at a time to commensurate with thickness and rapidly cooled or water quenched for optimal properties.