

# HASTELLOY<sup>®</sup> G-30<sup>®</sup> alloy

## Hardness

<b>Form</b>	<b>Hardness, HRBW</b>	<b>Typical ASTM Grain Size</b>
Sheet	81	1.5 - 4
Plate	80	0 - 3
Bar	78	0 - 2

All samples tested in solution-annealed condition.

HRBW = Hardness Rockwell "B", Tungsten Indentor.