

# HAYNES<sup>®</sup> 230<sup>®</sup> alloy

## Hardness and Grain Size

### Solution Annealed Room Temperature Hardness

<b>Form</b>	<b>Hardness, HRBW</b>	<b>Typical ASTM Grain Size</b>
Sheet	92	4 - 6.5
Plate	92	3 - 5
Bar	90	3 - 5

HRBW = Hardness Rockwell "B", Tungsten Indentor.